

# ARMACRETE C2



## DESCRIPTION

**ARMACRETE C2** is a water based, 100% colloidal silica dispersion for densifying concrete.

Of all the densifier types, the colloidal silicas have the smallest molecule size, allowing the best possible penetration of tight (low porosity) concrete surfaces such as polished concrete.

With a particle size of 12 microns, it provides a superior result, providing a stronger, higher concrete surface.

The densified concrete surface provides substantially reduced water penetration, also preventing rubber marking from vehicle tyres.

### 100% Colloidal Silica Dispersion Provides High Possible Penetration and Densification Result

## USE

It can be used on new and old concrete slabs to densify the concrete surface and reinforce the concrete slab.

It can be used at time of pour but generally is applied after the removal of the curing compound or at the commencement of the concrete polishing process.

## ADVANTAGES OF USE

- Water based
- Zero VOC
- Complies with green star- office design
- Improved concrete curing
- Improved waterproofing and stain resistance
- Eliminates dusting of concrete surfaces
- Increase abrasion resistance to the concrete surface
- Over trade compatible

## DIRECTIONS

Spray **ARMACRETE C2** onto the concrete surface using an airless spray unit.

Keep the surface wet for at least 15 minutes, brooming pooled excess surface liquid onto drier areas and adding additional **ARMACRETE C2** product if needed to maintain dampness.

After 1 hour using a squeegee to remove any excess material from the surface.

With regards to OH&S, extra care must be taken when moving around on the surface due to the slippery nature of the coating.





## PERFORMANCE GUIDE

Colloidal Silica densifiers have the smallest particle size in the concrete densifier product category.

This is not the molecule size, but the agglomerated macro particle size (i.e. lithium silicate is a larger molecular than potassium silicate but the agglomerate size in the solution is much smaller).

As the diagram below displays, the colloidal solution is an evenly distributed dispersion of individual particles and much finer again than traditional alkaline metal silicates (sodium/potassium/lithium silicate) clusters.

### Four Types of Synthetic Amorphous\* Silica

- Silica gels  hard aggregates
- Precipitated silica  grape clusters
- Fumed silica  chain-like
- Colloidal silica  primary particles



## ARMACRETE C2



### In order of particle size (and cost)

**Sodium Silicates > Potassium Silicates > Lithium Silicates > Colloidal Silica (particle size 6-12 nm)**

Even though sodium silicates and colloidal silicates share similar raw materials (salt + sodium hydroxide), the final particle sizes depend on the polymerization of the sub molecules in the reaction chemistry.

Colloidal silicas used in the **ARMACRETE C2** densifier molecule size ranges between 6-16 micron, with an average of 12 um.

**ARMACRETE C2** has been formulated to be like the other major colloidal densifier products on the market with similar pH, solids, and performance.

### SPECIFICATION CLAUSE

The coating should be applied (undiluted) in a single coat at the specified rate of 5m/L (0.2L/m<sup>2</sup>) to achieve film thickness to achieve the correct densification properties.

**ARMACRETE C2** must be applied on to the substrate at the coverage rates recommended as a minimum specification.

The surface must be kept wet with **ARMACRETE C2** product for at least 15 minutes after application.

If specified at higher rates then ensure that after sufficient time has passed for soakage/penetration, any excess material is removed to the surface before it dries.

All designated areas are to have a densifier compound applied to freshly finished concrete.

The curing compound will be colloidal silica dispersion.

The densifier compound is to be applied in accordance with the manufacturer's application instructions.

### LIMITATIONS

While the densification process vastly reduces water penetration, a penetrating sealer is recommended to provide full stain protection of the surface.

### COVERAGE

5 m<sup>2</sup> per litre (0.2L/m<sup>2</sup>) as supplied

### CLEAN UP

Water cleanup

### STORAGE

Store in cool, dry conditions, away from sources of heat and naked flames, in original, unopened packs.

If stored at high temperatures and/or high humidity conditions the shelf life may be reduced.

### PACKS

20L, 200L, 1000L

### ARMACRETE C2 - PDS OCT 2024

This Product Data Sheet (PDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this PDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the way, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Chemical House does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether in accordance with any advice, specification, recommendation, or information given by it.



#### Headquarters

9 Production Avenue, Molendinar

Queensland, 4214 Australia

Ph: +61 7 5594 0344

[www.chemicalhouse.com.au](http://www.chemicalhouse.com.au)